



EXTINGUISHING AGENTS- D EXTING. POWDER

		QTEC-D
Main Components		Alkali Chloride
Content	%	90
Bulk Density	g/ml	0,98-1,08
Sieve Analysis		
Retained on 125 µm		3-13
Retained on 63 µm	%	16-32
Retained on 40 µm		9-25
Moisture Content	%	≤0.10
Water Repellency		Positive
Resistance to Caking and Lumping		Positive
Fluidity	g/s	-
Thermal Stability		
From:	°C	-60
To:		+75

Physical Risks: No toxicological hazards, neither during handling nor during the application of the extinguisher. (Ecotoxicity Test EC₅₀)

Durability: Products' durability is guaranteed for at least 5 years, while no change or deformation in its properties occur and as long as manufacturer's instructions concerning handling and storage are followed.

QUÍMICA 21, S.L. reserves its right for any possible modification.