



EXTINGUISHING AGENTS- ABC EXTING. POWDER

QFIRE

Main Components		Phosphate and Sulphate										
Phosphate content	%	10	20	30	40	50	55	60	70	75	80	90
Bulk Density (*)	g/ml	0.84-.98	0.84-0.98	0.84-0.98	0,84-0,98	0,84-0,98	0,84-0,98	0,84-0,98	0,84-0,98	0,84-0,98	0,84-0,98	0,84-0,98
Sieve Analysis (*)												
Retained on 125 µm		15-25	15-25	15-25	15-25	15-25	15-25	15-25	15-25	15-25	15-25	15-25
Retained on 63 µm	%	22-38	22-38	22-38	22-38	22-38	22-38	22-38	22-38	22-38	22-38	22-38
Retained on 40 µm		12-28	12-28	12-28	12-28	12-28	12-28	12-28	12-28	12-28	12-28	12-28
Moisture Content (*)	%	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25	≤0,25
Water Repellency (*)		Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive
Resistance to Caking and Lumping (*)		Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive	Positive
Fluidity	g/s	<60	<60	<60	<60	<60	<60	<60	<60	<60	<60	<60
Thermal Stability												
From:	°C	-60	-60	-60	-60	-60	-60	-60	-60	-60	-60	-60
To:		+85	+85	+85	+85	+85	+85	+85	+85	+85	+85	+85

(*)All the products are manufactured according to the European Standard UNE-EN 615:2009

Physical Risks: No toxicological hazards, neither during handling nor during the application of the extinguisher. (Ecotoxicity Test EC₅₀)

Durability: Products' durability is guaranteed for at least 5 years, while no change or deformation in its properties, occur and as long as manufacturer's instructions concerning handling and storage are followed.

QUÍMICA 21, S.L. reserves its right for any possible modification.